

**TECHNICAL DATA SHEET**  
**(SPLENDOR SP65 PU FOAM)**

**SPLENDOR SP-65 PU FOAM**, which is based on moisture curing polyurethane, containing safety propellant, is used to seal gaps and crevices with very high expansion yield **UP TO 60~65 LITERS**, the post-expansion is quite low to prevent deformation. The foam that dispenses from aerosol can is moisture cured and draws humidity from the air for cure. PU foam is widely used for filling joints between walls, ceilings, floors and gaps around pipes, windows and doorframes. Foam can be cut once fully cured, provides excellent bond to lumber, plywood, concrete, metals, masonry and other substrates.

**SPLENDOR SP-65 PU FOAM** is for all-season, all weather, multi-purpose use such as:

- Mounting of window and door frames
- Sealing of all types of cracks and holes
- Insulation of water-pipe network, central heating
- Soundproofing of partition walls, car and boat cabins etc.

**PRODUCT FEATURES**

- Economically insulates, fills, seals and bonds
- Easy to use
- Bonds to and seals most popular construction materials, wood, concrete, plaster, plumbing etc.
- Excellent for interior and exterior applications
- Durable airtight seal-stops air infiltration, drafts and energy loss
- High insulating value-saves energy and money

**TECHNICAL DATA:**

|                                  |                                   |
|----------------------------------|-----------------------------------|
| Basic Component                  | Polyurethane                      |
| Type                             | Gun type and straw type available |
| Appearance                       | Foam                              |
| Color                            | Light yellow                      |
| Tack-Free Time (min)             | 8~10                              |
| Cutting Time (min)               | 30 (+25℃)                         |
| Density (kg/m <sup>3</sup> )     | 16~20                             |
| Yield (L)                        | 60~65                             |
| Thermal conductivity (mW/ (m K)) | <34                               |
| Adhesive strength (kPa)          | >80                               |
| Tensile strength(kPa)            | >30 (10%)                         |
| Compressive strength(kPa)        | >120                              |
| Close cells content%             | 45~52                             |
| Water absorption(up to 24h)      | ≤1.5% (no epidermis)              |
| Fire Class of the cured foam     | B3                                |

|  |  |
|--|--|
| Dimensional stability (23°C)               | 0~1.0%(foaming direction)                    |
|  | 0~1.8%(flat direction)                       |
| Environment                                | Contains no CFC's, no HCFC's, Ozone friendly |
| Toxicity of cured foam                     | Non-toxicity                                 |
| Service temperature range of cured foam °C | -40 to +100                                  |
| Processing temperature range(°C)           | 0 to +40                                     |
| Shelf life (month)                         | 18   |

### **PREPARATION FOR USE**

Substrate must be clean, firm, free of loose particles and free of dust, grease and mold release agents. Surfaces not to be foamed must be protected. Shake cans well before using.

### **HOW TO USE**

1. Shake can well to make the foam ready for use
2. Clean the substrate and spray some water on it
3. Screw foam dispenser on tightly and turn can upside down
4. Vertical fills the gaps from the bottom upwards
5. Foam is tack-free (dry to the touch) in 8 minutes in temperatures between +18°C and +25°C (65°F ~77°F). Higher temperatures will result in faster curing times
6. Remove fresh foam over spray with Splendor Foam Cleaner or solvents such as acetone. Cured foam can only be removed mechanically.

**Remark:** For gun/professional foam, an additional foam gun dispenser is needed to spray (Needs to buy separately). In such case, you may also need to buy foam cleaner to clean the gun adapter after use.

### **IMPORTANT NOTE**

Contents are under pressure. Do not puncture or incinerate. Do not place in hot water or near radiators, stoves or other sources of heat.

Use only in well-ventilated areas. Wear impervious gloves, protective eyewear, and suitable work clothes when using. Read all instructions and safety information (MSDS) prior to use of any product. The product contains no formaldehyde. Cured foam is non-toxic.

### **SAFETY ADVICE**

Keep out of children's reach

Keep upright

Shelter from direct sunlight

Do not expose to temperatures exceeding 50°C

Do not pierce or burn even after use

No smoking during the whole spraying procedure

For safety reasons, please wear protective gloves as well as goggles before using Splendor SP65 PU Foam, and do not draw them off until the whole procedure is finished.

### **PRODUCT STORAGE**

Store in cool, dry area. Do not expose to open flame. Excessive heat can cause premature aging of components resulting in shorter shelf life. Splendor SP65 PU Foam is reusable by following product instructions.